



# TEST REPORT

DATE: 07-18-2019

Page 1 of 2

TEST NUMBER: 0258736

<b>CLIENT</b>	Palziv North America
---------------	----------------------

<b>TEST METHOD CONDUCTED</b>	ASTM C518 (R-Value) Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
<b>IDENTIFICATION</b>	ECF Eco Cork Foam

### TEST METHOD

The material was tested in accordance with the ASTM International Test Method C518, Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus. This test method covers the measurement of steady state thermal transmission through flat slab specimens using a heat flow meter apparatus. The heat flow meter apparatus is used widely because it is relatively simple in concept, rapid, and applicable to a wide range of test specimens. This is a comparative, or secondary, method of measurement since specimens of known thermal transmission properties are used to calibrate the apparatus. Properties of the calibration specimens, obtained from a recognized national standards laboratory, are traceable to an absolute measurement method.

The heat flow meter apparatus establishes steady state one-dimensional heat flux through a test specimen between two parallel plates at constant but different temperatures. By appropriate calibration of the heat flux transducer with calibration standards and by measurement of the plate temperatures and plate separation. Fourier's law of heat conduction is used to calculate thermal conductivity and thermal resistance.

This test method provides a rapid means of determining the steady-state thermal transmission properties of thermal insulations and other materials with a high level of accuracy when the apparatus has been calibrated appropriately. Proper calibration of the heat flow meter apparatus requires that it be calibrated using specimens having thermal transmission properties determined previously by Test Methods C 177 or C 1114.

The thermal transmission properties of specimens of a given material or product may vary due to variability of the composition of the material; be affected by moisture or other conditions; change with time; change with mean temperature and temperature difference; and depend upon the prior thermal history. It must be recognized, therefore, that the selection of typical values of thermal transmission properties representative of a material in a particular application should be based on a consideration of these factors and will not apply necessarily without modification to all service conditions.

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.



### TEST REPORT

DATE: 07-18-2019

Page 2 of 2

TEST NUMBER: 0258736

<b>CLIENT</b>	Palziv North America
---------------	----------------------

<b>TEST METHOD CONDUCTED</b>	ASTM C518 (R-Value) Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
------------------------------	--



<b>DESCRIPTION OF TEST SAMPLE</b>	
<b>IDENTIFICATION</b>	ECF Eco Cork Foam

#### TEST RESULTS

Prior to testing, the R-Matic was calibrated using the National Institute of Standards and Technology (NIST) Standard Reference Material 1453, Expanded Polystyrene Board. SRM 1453 has a known Thermal Resistance of  $2.254 \pm 0.028 \text{ h}\cdot\text{ft}^2\cdot^\circ\text{F}\cdot\text{Btu}^{-1}$  at a thickness of 0.528 inch at mean temperature of 75° F.

#### U.S. Customary Units

Mean Temperature	75.00	°F
Thickness	0.125	inch
Density as Tested	7.50	lbs/ft <sup>3</sup>
Thermal Conductivity, $\lambda$	0.2586	Btu in./h ft <sup>2</sup> F
Thermal Resistance, $R$	0.483	F ft <sup>2</sup> h/Btu
Heat Flux, $q$	103.92	Btu/h ft <sup>2</sup>
U Value, $U$	2.069	Btu/(h ft <sup>2</sup> F)
Test Duration	103	minutes

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.